

## ULTRA

### DESCRIPTION

Extended durability opaque protection for exterior wood based on a pure acrylic resin which is exceptionally flexible, water repellent, weatherproof and durable. Ultra is moisture regulating and will not crack, peel or blister. Ultra gives excellent protection to new, previously preservative treated, stained or painted timber.

### EXAMPLES OF USE

Exterior cladding, weatherboarding, windows, doors, facias, log cabins, conservatories and garden furniture.

### TECHNICAL DATA

Solids Volume: approx. 43%.  
Density: 1.2kg/ltr  
Base Paints: A and C

### Colour Range

Available in white, the complete Tikkurila Professional and Façade Colour Ranges, plus most of the British Standard, RAL and NCS Colour Ranges. Note: Colour shades will not fully develop until the paint is completely dry.

### SPECIFICATIONS

#### Preparation

Surfaces must be clean, dry, and free from grease, dirt, oil, wax, rust, all loose material and surface contamination. Use recommended Tikkurila products for mould removal and cleaning. Treat knots and resinous areas with Tikkurila Knotting Lacquer. Use recommended Tikkurila fillers for filling cracks, nail holes, blemishes, etc. Ensure that existing glossy, gloss painted and filled surfaces are thoroughly flatted down. Ensure that all surfaces are thoroughly prepared prior to priming and painting. Make sure that timber cladding, weatherboarding and timber glazing beads, etc., are adequately fastened with non-corrosive fixings.

Note: Discoloration of paint especially noticeable with light colours may occur over knots and resinous areas present in the wood. Particular attention with regards to preparation should be given to wood such as Oak, Teak, Cedar, Douglas Fir, Mahogany and Idigbo, etc., which contain oil and water-soluble tannin which may impair the drying, hardening or adhesion of surface coatings and discolour the finished surface.

#### Priming

Prime new bare wood overall and spot prime all bare areas on previously painted wood with Valtti Base Priming Oil. Use Otex or Unica Adhesion Primer on wood that contains substances, which may 'bleed through', and cause staining to the finished surface. Prime all bare metal and potential rust spots with Unica Metal Primer or Rostex Super

Note: A priming coat of Valtti Base should be applied to all exterior wood which has not been pre-treated or vacuum impregnated with an approved wood preservative. Apply liberally on end grain.

## ULTRA

<b>APPLICATION</b>	Methods: brush or spray. Polyester and nylon paint brushes are best suited for the application of Ultra. For airless spray: use a 0.013" (0.33mm) spray tip. Thinning: if necessary by up to 10% with water.
<b>Painting Conditions</b>	All surfaces to be painted must be dry, the moisture content of the wood below 20%, the temperature of the air at least +5°C, and the relative humidity of the air below 80%.
<b>Painting</b>	Stir the paint thoroughly and apply two coats of Ultra overall.
<b>Coverage</b>	Smooth wood: 8-10m <sup>2</sup> /litre per coat. Sawn wood: 4-8m <sup>2</sup> /litre per coat. Wet-film thickness approximately 100-250µm per coat, dry-film approximately 40-100µm per coat. Actual spreading rates will depend upon many factors including texture, porosity and moisture content of the substrate.
<b>Drying Times</b>	At 23°C and 50% relative humidity of the air: normally touch-dry in one hour and recoatable after 2 hours. Low temperature and high humidity will make drying times longer.
<b>Cleaning of Tools</b>	Clean with water immediately after use.
<b>MAINTENANCE</b>	Depending upon exposure and elevation, one coat of Ultra is normally sufficient after 8-10 years.
<b>PREVENT ENVIRONMENTAL DAMAGE</b>	Empty cans should be recycled or disposed of in accordance with local regulations. Liquid waste should be destroyed according to the local regulations for hazardous waste.
<b>TRANSPORT</b>	ADR/RID - Protect from frost.

ins300104/lko/esi251-s

The above information, based on laboratory tests and practical experience, has been proved valid at the date marked on the product data sheet. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As a manufacturer we cannot be responsible for any damages caused by using the product against our instructions or for inappropriate purposes.

For further information or advice contact:

Holman Specialist Paints Ltd  
1 Central Trading Estate  
Signal Way  
Swindon SN3 1PD

Tel 01793 511537 FAX 01793 431142

[www.holmanpaints.co.uk](http://www.holmanpaints.co.uk)

e-mail [sales@holmanpaints.co.uk](mailto:sales@holmanpaints.co.uk)